Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-07-24-12** **Date: 28-07-2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Bharath nagara in Ward No 11 (Kuvempunagara) in Vidyaranyapura Sub Division.
Agency	:	Sri.S.Venkateshappa, #530, Kaliyamma temple road, Kuvempunagara 2nd stage, Bangalore-560014.
Customer's Reference	:	BBMP/EE/BTP/WO/57/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	24-07-2018
Sample ID No	:	2018-07-24-12 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	25-07-2018
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.95	–
2	Finess by Air permeablity method (m^2/kg,Min)	285.4	225m^2/kg, Min
3	Density (gm/cc)	3.12	–
4	Standard Consistency (%)	29.5%	Not specified
5	Initial Setting time (minutes)	145 minutes	Not less than 30 minutes
6	Final Setting time (minutes)	240 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method) (mm)	1.5mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-07-24-12** **Date: 22-08-2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Bharath nagara in Ward No 11 (Kuvempunagara) in Vidyaranyapura Sub Division.
Agency	:	Sri.S.Venkateshappa, #530, Kaliyamma temple road, Kuvempunagara 2nd stage, Bangalore-560014.
Customer's Reference	:	BBMP/EE/BTP/WO/57/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	24-07-2018
Sample ID No	:	2018-07-24-12 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	25-07-2018
Environmental Conditions during test	:	Temperature: 26˚C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results (N/mm^2)	Requirement as per IS 12269: 2013
1	3 Days	28.5N/mm2	Not less than 27 N/mm^2
2	7 Days	39.0N/mm2	Not less than 37 N/mm^2
3	28 Days	56.5N/mm2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-07-24-12** **Date: 28-07-2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Bharath nagara in Ward No 11 (Kuvempunagara) in Vidyaranyapura Sub Division.
Agency	:	Sri.S.Venkateshappa, #530, Kaliyamma temple road, Kuvempunagara 2nd stage, Bangalore-560014.
Customer's Reference	:	BBMP/EE/BTP/WO/57/2018-19
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	24-07-2018
Sample ID No	:	2018-07-24-12 /02(a)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	24-07-2018

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	232	232	1.5	98.5	90-100
3	20 mm	5334	5566	37.1	62.9	30-70
4	10 mm	4665	10231	68.2	31.8	10-35
5	4.75 mm	4355	14586	97.2	2.8	0-5
6	Pan	414	15000	100.0	0	---

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL PRO Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2018-07-24-12** **Date: 28-07-2018**

Sample ID No : 2018-07-24-12 /02(a)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	**12.4**	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	**11.7**	
3	Specific Gravity	**2.69**	_
4	Bulk Density(Loose) (Kg/l)	**1.49**	_
5	Bulk Density(Compacted) (Kg/l)	**1.54**	_
6	Water Absorption(%)	**0.24**	_

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

****End of Report****

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-07-24-12** **Date: 28-07-2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Bharath nagara in Ward No 11 (Kuvempunagara) in Vidyaranyapura Sub Division.
Agency	:	Sri.S.Venkateshappa, #530, Kaliyamma temple road, Kuvempunagara 2nd stage, Bangalore-560014.
Customer Reference	:	BBMP/EE/BTP/WO/57/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	24-07-2018
Sample ID No	:	2018-07-24-12 /02(b)
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	24-07-2018

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	245	245	4.9	95.1	90-100
3	10 mm	2560	2805	56.1	43.9	25-55
4	4.75 mm	2033	4838	96.8	3.2	0-10
5	Pan	162	5000	100	0	–

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore -97

CIVIL Pro Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2018-07-24-12** **Date: 28-07-2018**

Sample ID No : 2018-07-24-12 /02(b)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	**13.2**	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	**12.6**	
3	Specific Gravity	**2.66**	_
4	Bulk Density(Loose) (Kg/l)	**1.54**	_
5	Bulk Density(Compacted) (Kg/l)	**1.58**	_
6	Water Absorption(%)	**0.22**	_
7	Aggregate crushing Value(%)	**24.5**	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	**22.8**	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2018-07-24-12** **Date: 28-07-2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Bharath nagara in Ward No 11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.S.Venkateshappa, #530, Kaliyamma temple road, Kuvempunagara 2nd stage, Bangalore-560014.

Customer's Reference : BBMP/EE/BTP/WO/57/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-07-2018

Sample ID No : 2018-07-24-12 /03

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 24-07-2018

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	21	21	2.1	97.9	90-100	90-100	90-100	95-100
3	2.36 mm	185	206	20.6	79.4	60-95	75-100	85-100	95-100
4	1.18 mm	201	407	40.7	59.3	30-70	55-90	75-100	90-100
5	600 micron	168	575	57.5	42.5	15-34	35-59	60-79	80-100
6	300 micron	229	804	80.4	19.6	5-20	8-30	12-40	15-50
7	150 micron	153	957	95.7	4.3	0-10	0-10	0-10	0-15
8	Pan	43	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2018-07-24-12** **Date: 28-07-2018**

Sample ID No : 2018-07-24-12 /03

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.42	–
2	Specific Gravity	2.53	–
3	Material finer than 75 micron(%)	3.9	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore -97

Format No: CP/TF/01

TEST RESULTS OF STEEL

Lab ID : **CP-2018-07-24-12** **Date: 26-07-2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Bharath nagara in Ward No 11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.S.Venkateshappa, #530, Kaliyamma temple road, Kuvempunagara 2nd stage, Bangalore-560014.

Customer's Reference : BBMP/EE/BTP/WO/57/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 24-07-2018

Sample ID No : 2018-07-24-12 /04

Sample Type : Sunvik

Reference to BIS codes : IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.

Date of test: : 25-07-2018

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	8	0.387	542	674	19.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	10	0.624	572	686	20.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	12	0.884	587	697	20.0%	Satisfactory	Satisfactory

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID	:	**CP-2018-07-24-12**	**Date: 28-07-2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.	
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.	
Project Name	:	Improvements to Roads and Drains at Bharath nagara in Ward No 11 (Kuvempunagara) in Vidyaranyapura Sub Division.	
Agency	:	Sri.S.Venkateshappa, #530, Kaliyamma temple road, Kuvempunagara 2nd stage, Bangalore-560014.	
Customer's Reference	:	BBMP/EE/BTP/WO/57/2018-19	
Source of Sample	:	Sample supplied by Agency	
Sample Condition	:	Satisfactory	
Date of Receipt	:	24-07-2018	
Sample ID No	:	2018-07-24-12 /06	
Sample Type /Size	:	Precast Cover Slab	
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete	
Date of test	:	25/07/2018	

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	75.23	100.37	2.724	4444	96.4	21.7	20.2	25.2
2	Cover Slab-2	75.18	100.55	2.746	4438	95.1	21.4	19.9	24.9
3	Cover Slab-3	75.29	100.28	2.778	4451	94.8	21.3	19.8	24.8

Note:

The results pertain to the samples received and tested.
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-08-01-05** **Date: 07/08/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Bharath nagara in Ward No 11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.S.Venkateshappa, #530, Kaliyamma temple road, Kuvempunagara 2nd stage, Bangalore-560014.

Customer's Reference : BBMP/EE/BTP/WO/57/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 01-08-2018

Sample ID No : 2018-08-01-05 /01

Customer ID : RMC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 07/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)³	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RMC	M20	31/07/2018	07/08/2018	149.91 X 150.17 X 151.53	22512	8.555	409.8	18.2	18.5
2	RMC	M20	31/07/2018	07/08/2018	151.05 X 149.79 X 149.35	22627	8.531	422.2	18.7	
3	RMC	M20	31/07/2018	07/08/2018	150.14 X 149.45 X 151.12	22439	7.950	415.5	18.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-08-01-05** **Date: 28/08/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Bharath nagara in Ward No 11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.S.Venkateshappa, #530, Kaliyamma temple road, Kuvempunagara 2nd stage, Bangalore-560014.

Customer's Reference : BBMP/EE/BTP/WO/57/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 01-08-2018

Sample ID No : 2018-08-01-05 /02

Customer ID : RMC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 28/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RMC	M20	31/07/2018	28/08/2018	151.51 X 150.01 X 150.30	22727	8.263	532.8	23.4	23.2
2	RMC	M20	31/07/2018	28/08/2018	151.76 X 151.56 X 151.30	23001	8.581	516.5	22.5	
3	RMC	M20	31/07/2018	28/08/2018	151.37 X 149.58 X 150.91	22641	8.239	535.0	23.6	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-08-01-05** **Date: 07/08/2018**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Bharath nagara in Ward No 11 (Kuvempunagara) in Vidyaranyapura Sub Division.

Agency : Sri.S.Venkateshappa, #530, Kaliyamma temple road, Kuvempunagara 2nd stage, Bangalore-560014.

Customer's Reference : BBMP/EE/BTP/WO/57/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 01-08-2018

Sample ID No : 2018-08-01-05 /03

Customer ID : RMC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 07/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RMC	M20	31/07/2018	07/08/2018	151.54 X 149.78 X 150.06	22698	8.526	429.8	18.9	18.8
2	RMC	M20	31/07/2018	07/08/2018	150.42 X 151.79 X 149.41	22832	8.161	431.4	18.9	
3	RMC	M20	31/07/2018	07/08/2018	149.14 X 150.33 X 151.58	22421	8.396	414.4	18.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	CP-2018-08-01-05 **Date: 28/08/2018**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Bharath nagara in Ward No 11 (Kuvempunagara) in Vidyaranyapura Sub Division.
Agency	:	Sri.S.Venkateshappa, #530, Kaliyamma temple road, Kuvempunagara 2nd stage, Bangalore-560014.
Customer's Reference	:	BBMP/EE/BTP/WO/57/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	01-08-2018
Sample ID No	:	2018-08-01-05 /04
Customer ID	:	RMC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	28/08/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	RMC	M20	31/07/2018	28/08/2018	151.93 X 149.71 X 150.96	22745	8.510	543.5	23.9	23.2
2	RMC	M20	31/07/2018	28/08/2018	150.60 X 150.97 X 149.38	22737	8.138	513.3	22.6	
3	RMC	M20	31/07/2018	28/08/2018	150.79 X 150.68 X 149.59	22721	8.473	526.2	23.2	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97.

CIVIL PRO Sig..... Date..... BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |